


# Technical Data Sheet

## StoColor Lastic

Facade paint on a emulsion base, cold-elastic



### Characteristics

#### Area of application

- exterior
- as an intermediate coat and finish in the Sto crack repair system for cracks up to max. 1.0 mm width
- with a double paint coat suitable for crack widths up to max. 1.2 mm, class A3 in accordance with EN 1062-7
- optimal crack bridging only possible with a double paint coat
- not suitable for horizontal or sloping surfaces
- not suitable for lime-containing substrates and surfaces of mortar groups PI in accordance with DIN 18550 and CS1 in accordance with EN 998-1 with strengths less than 1 N/mm<sup>2</sup>
- not suitable for areas that are contaminated with plasticiser and paraffin (e.g. from not fully removed paint remover)

#### Properties

- UV-crosslinking
- highly elastic
- very high resistance to soiling for such a highly elastic facade paint
- very good hiding power
- very highly water-repellent
- water vapour permeable
- cold-elastic

#### Appearance

- silk matt

#### Information/notes

- with encapsulated film protection

### Technical data

Criterion	Standard / test specification	Value/ Unit	Notes
Density	EN ISO 2811	1.3 - 1.5 g/cm <sup>3</sup>	
Diffusion-equivalent air layer thickness	EN ISO 7783	1.6 m	V3 low

# Technical Data Sheet

## StoColor Lastic

Water permeability rate w	EN 1062-1	< 0.1 kg/(m <sup>2</sup> h <sup>0.5</sup> )	W3 low
Water vapour diffusion-equivalent air layer thickness μ	EN ISO 7783	3,900	average value
Gloss	EN 1062-1	Matt	G3
Dry layer thickness	EN 1062-1	410 μm	E5 > 400
Grain size	EN 1062-1	< 100 μm	S1 fine

The characteristic values stated are average values or approximate values. Due to the natural raw materials in our products, the stated values can vary slightly in the same delivery batch; this does not affect the suitability of the product for its intended use.

### Substrate

#### Requirements

The substrate must be firm, dry, clean, load-bearing, and free from sinter layers, efflorescence and release agents. Damp or not fully cured substrates can lead to defects in the following coatings, e.g. bubble formation, cracks.

#### Preparations

Check whether existing coatings are load-bearing. Remove any non load-bearing or structurally weak coatings.

### Application

#### Application temperature

Lowest temperature of substrate and air: +5 °C  
 Highest temperature of substrate and air: +30 °C

The substrate temperature must be above the dew point temperature. The recommended difference is +3 °C.

#### Material preparation

Usage as an intermediate coat: dilute with max. 2 % water.  
 Usage as finish: undiluted.

Dilute with as little water as possible to achieve application consistency. Stir the material well before application. If applying the material by machine or pump, adjust the application consistency accordingly. Do not dilute intensely tinted material, or only use very little water. Too much dilution impairs the properties of the material, e.g. with regard to application, hiding power, and colour shade intensity.

#### Consumption

Type of application	Approx. consumption	
per paint coat	0.35 - 0.45	l/m <sup>2</sup>
for 2 coats	0.70 - 0.90	l/m <sup>2</sup>

Material consumption depends on the application, substrate, and consistency, among other factors. The stated consumption values are only to be used as a guide. If required, determine precise consumption values on the basis of the specific project.

# Technical Data Sheet

---

## StoColor Lastic

<b>Coating build-up</b>	<p>Primer: Depending on the type and condition of the substrate, it may be necessary to apply consolidating, absorbency-regulating prime coatings. If using on a mineral substrate, we recommend using an absorbency-equalising and adhesion-promoting primer.</p> <p>Note: If the primer is omitted, this can impair the application properties and the product's appearance.products: e.g. StoPrim Micro, StoPlex W</p> <p>Intermediate coat: StoColor Lastic</p> <p>Finish: StoColor Lastic</p> <p>Depending on the substrate and colour shades, further paint coats are necessary.</p> <p>The technical data are based on a double paint coat.</p>
-------------------------	--

<b>Application</b>	<p>by paint brush, by roller The product is easy and smooth to apply.</p>
--------------------	---

<b>Drying, curing, ready for next coat</b>	<p>Higher humidity, lower temperatures, and low air exchange prolong the curing and drying times.</p> <p>During unfavourable weather conditions, apply suitable protective measures (e.g. protection against rain) to any facade surface which is to be treated or which has been freshly completed.</p> <p>At +20 °C temperature (air and substrate) and 65 % relative air humidity: over-coatable after approx. 12 hours.</p>
--	---

<b>Cleaning the tools</b>	Clean tools with water immediately after use.
---------------------------	---

### Delivery

<b>Colour shade</b>	<p>white, tintable in accordance with the StoColor System</p> <p>Tinted material: Before application, check that the material corresponds to the colour shade ordered. Slight colour shade deviations compared with previous deliveries are possible. Only use deliveries with the same batch number on one surface. Mix different batches before application.</p> <p>Colour stability: The effects of weather, moisture, UV radiation, and deposits can alter the surface of the coating. Changes in colour shade are possible. The change process is</p>
---------------------	--

# Technical Data Sheet

---

## StoColor Lastic

dynamic and influenced by climatic conditions and exposure. National regulations, data sheets etc. apply.

Extender material breakdown:

Mechanical stress can damage the extenders in the material and lead to lighter marks. This does not influence the product quality or functionality.

Colour accuracy:

Different weather and project conditions influence colour shade accuracy and colour shade uniformity. Avoid the following conditions (a - d) in every case:

- a) uneven absorbency of the substrate
- b) different levels of substrate moisture over an area
- c) partly very different alkalinity and/or substances in the substrate
- d) direct sunlight with sharp, clear shadows on a still-damp coating

Washout of processing aids:

If water such as condensation, fog, or rain comes into contact with not fully dry coatings, processing aids may be released from the coating and build up on the surface. Whether the effect is strongly visible or not depends on the intensity of the colour shade. This does not influence the product quality. The effects disappear when the surface is exposed to further weathering.

---

<b>Tintable</b>	It can be tinted by the user with StoColor Tint or with max. 1 % StoTint Aqua.
-----------------	--

---

<b>Packaging</b>	pail
------------------	------

### Storage

<b>Storage conditions</b>	Store tightly sealed in frost-free conditions. Protect from heat and direct sunlight.
---------------------------	---

<b>Storage life</b>	The quality of the product in its original container is guaranteed until the maximum storage life has expired. The storage life information is included in the batch number on the container. Explanation of batch no.: digit 1 = last digit of the year, digits 2 + 3 = calendar week Example: 1450013223 - storage life ends week 45in 2021
---------------------	--

### Identification

<b>Product group</b>	Facade paint
----------------------	--------------

### Composition

In accordance with the VdL directive (German Paint and Printing Ink Association) on coating materials for buildings  
polymer dispersion  
titanium dioxide  
mineral extenders

# Technical Data Sheet

---

## StoColor Lastic

silicate extenders  
 water  
 glycol ether  
 aliphatics  
 alcohols  
 thickener  
 anti-foaming agents  
 dispersing agent  
 wetting agents  
 coating protection agent based on isoproturone/terbutryn  
 coating protection agent based on 3-Iodo-2-propynyl butylcarbamate (IPBC)  
 storage protection agent based on BIT/ZPT

---

### Safety

This product is subject to compulsory labelling in accordance with the current EU regulation.

Observe the Safety Data Sheet!

Safety instructions refer to the ready-to-use, unapplied product.

Harmful to aquatic life with long lasting effects. Avoid release to the environment. Contents/container to be disposed of through approved disposal contractor or taken to municipal collection point.

### EUH208

Contains 1,2-benzisothiazol-3(2H)-one. May produce an allergic reaction.

These are preservatives.

### Special notes

The information in this Technical Data Sheet serves to ensure the product's intended use, or its suitability for use, and is based on our findings and experience. Users are nevertheless responsible for establishing the product's suitability and use. Applications not specifically mentioned in this Technical Data Sheet are permissible only after prior consultation. Where no approval is given, such applications are at the user's own risk. This applies in particular when the product is used in combination with other products.

When a new Technical Data Sheet is published, all previous Technical Data Sheets are no longer valid. The latest version is available on the Internet.

Sto SE & Co. KGaA  
 Ehrenbachstr. 1  
 79780 Stühlingen / Germany  
 Phone: +49 7744 57-0  
 Fax: +49 7744 57-2178  
 Infoservice.export@sto.com

# Technical Data Sheet

---

## StoColor Lastic

[www.sto.com](http://www.sto.com)